

**Material Data Sheet: RKFT- EPDM - O- 80 Black****APPLICATIONS**

- Gasket / Seal for automotive, electronics, construction, HVAC etc.
- Packaging for medicine equipment, glass, furniture etc.
- Insulation for cooler, air conditioner, freezer, construction, Engineering
- Sealing material for sound-proof,

Classification	ASTMD-1056	2A0	A2	B2	C2	F1	M	P	
Compliant according	Guideline 2011/65/EU (RoHS)	&	Regulation (EG) Nr. 1907/2006 (REACH)	&	Conflict Mineral Reporting Template (CMRT)				
Material Base	Ethylene – Propylene Diene –Monomer						ISO 1629		
Density	80 (±20) kg/m ³						ISO 845		
General Description	Semi closed cell, soft-elastic cellular rubber Cell size about 0.2 - 0.6mm						ASTM –D 1056		
Corrosion resistance	On bare Cu: strong corrosion On bare Ag: strong corrosion						DIN 53 428		
Temperature Range	-40°C to 100°C/ short time/ to +120 °C						without standard		
Compression Set	23 °C, 50%: ≤ 5% (after 0,5 h), ≤ 3% (after 24 h) 40 °C, 50%: ≤ 10% (after 0.5 h), ≤ 5% (after 24h)						ASTM –D 1056		
Linear shrinkage	≤ 5% (3 h at 80 °C and 6,3 mm thickness)						WSK-M2D419-17		
Compression-deflection	≤ 5 kPa (at 25% compression) ≤ 10 kPa (at 50%compression)						ASTM – D 1056		
Tensile strength	≥ 100 kPa						ISO 1798		
Elongation at break	≥ 150%						ISO 1798		
Electrical conductivity	> 10 ¹² Ωcm (test specimen: 120 x 120 x 10 mm; voltage: 100 V)						ASTM D991-89		



ROOP KOEPP FOAM TECHNOLOGIES PVT. LTD.

An Indo-German Joint Venture

Thermal conductivity	$\leq 0,05$ W/mK (at appr. 50% compression)	ISO 8302
Outdoor exposure	Very good weather resistance	ISO 877
Ozone resistance	Resistant to cracking (0)	ISO 1431-1
Form of delivery	<p>Block size with production skin minimum 2,000 (78.74) x 1,000 (39.37) x 50 (1.97) mm (in), Without skin. The material can be further processed by splitting, cutting, sawing, punching, gluing, milling, grinding and coating with adhesives.</p> <p>To split a stable sheet, a minimum thickness of 3 mm is required. The Determination of linear dimensions as per Tolerance Standard .</p>	
Resistances	<p>Oil = medium Ozone = very good Air + UV = very good</p> <p>Detailed information can only be obtained after formal testing in individual cases.</p>	
Remarks	<p>The material is very soft and flexible. Furthermore, it shows excellent acoustic insulation properties. According to EN ISO 10634-2, the calculated noise dampening reaches about 45% at 1000 Hz and a material thickness of 10 mm.</p>	
Suggestions for disposal	<p>It does not contain hazardous compounds such as cadmium, lead, CFCs, formaldehyde, etc. which require compliance to waste disposal regulations from 27/04/2009.</p> <p>Under the observance of local waste disposal regulations, it may therefore be disposed of as household waste on landfills or domestic waste incineration plants.</p>	

Note:- All RKFT products are as per the Material Data Sheet. This does not absolve users from the responsibility of conducting their own tests. We do not provide any product liability or recall related support.

ROOP KOEPP FOAM TECHNOLOGIES PVT. LTD.

Plot No 139, Roz-Ka-Meo Industrial Area, Sohna, Distt. Mewat (Nuh) 122103, Haryana, India.

E-Mail: sales@roopkoepp.com, Web: www.roopkoepp.com