



Material Data Sheet: RKFT-EPDM-OL Black

Page 1 of 2

APPLICATIONS

- Gasket / Seal for Automotive, Electronics, Construction, HVAC etc.
- Packaging for Medicine equipment, Glass, Furniture etc.
- Insulation for Cooler, Air Conditioner, Freezer, Construction, Engineering
- Sealing material for sound-proof

Classification	ASTMD-1056	2A0	A2	B2	C2	F1	M	P
Fire behavior	Based on FMVSS 302 Passed at 8.0 mm thickness							
Compliant according	Guideline 2011/65/EU	&		Regulation (EG) Nr. 1907/2006 (REACH)	&		Conflict Mineral Reporting Template	

Material Base	Ethylene–Propylene Diene–Monomer	ISO 1629
Density	80 (± 20) kg/m ³	ISO 845
General Description	Semi closed cell, Soft-elastic cellular rubber	ASTM – D 1056
Corrosion resistance	On bare Cu: strong corrosion On bare Ag: strong corrosion	DIN 53 428
Temperature Range	-40°C to 100°C/ short time/ to +120 °C	without standard
Compression Set	23 °C, 50%: $\leq 5\%$ (after 0,5 h), $\leq 3\%$ (after 24 h) 40 °C, 50%: $\leq 10\%$ (after 0.5 h), $\leq 5\%$ (after 24h)	ASTM – D 1056
Linear shrinkage	$\leq 5\%$ (3 h at 80 °C and 6,3 mm thickness)	WSK-M2D419-17
Compression-deflection	≤ 5 KPa (at 25% compression) ≤ 10 KPa (at 50% compression)	ASTM – D 1056
Tensile strength	≥ 100 KPa	ISO 1798
Elongation at break	$\geq 150\%$	ISO 1798



ROOP KOEPP FOAM TECHNOLOGIES PVT. LTD.

An Indo-German Joint Venture

Flammability	Passed for 8 mm.	FMVSS 302
Electrical conductivity	$> 10^{12} \Omega\text{cm}$ (test specimen: 120 x 120 x 10 mm; voltage: 100 V)	ASTM D991-89
Thermal conductivity	$\leq 0,05 \text{ W/mK}$ (at appr. 50% compression)	ISO 8302
Outdoor exposure	Very good weather resistance	ISO 877
Ozone resistance	Resistant to cracking (0)	ISO 1431-1
Sheet Size/Thickness	Block size with production skin minimum 2,000 (78.74) x 1,000 (39.37) x 50 (1.97) mm (in), Without skin. The material can be further processed by splitting, cutting, sawing, punching, gluing, milling, grinding and coating with adhesives. To split a stable sheet, a minimum thickness of 3 mm is required. Determination of linear dimensions as per DIN EN ISO 1923 Standard .	
Resistances	Oil = medium Ozone = very good Air + UV = very good Detailed information can only be obtained after formal testing in individual cases.	
Remarks	The material is very soft and flexible. Furthermore, it shows excellent acoustic insulation properties. According to EN ISO 10634-2, the calculated noise dampening reaches about 45% at 1000 Hz and a material thickness of 10 mm.	
Suggestions for disposal	It does not contain hazardous compounds such as cadmium, lead, CFCs, formaldehyde, etc. which require compliance to waste disposal regulations from 27/04/2009. Under the observance of local waste disposal regulations, it may therefore be disposed of as household waste on landfills or domestic waste incineration plants.	

Note:- All RKFT products are as per the Material Data Sheet. This does not absolve users from the responsibility of conducting their own tests. We do not provide any product liability or recall related support.

ROOP KOEPP FOAM TECHNOLOGIES PVT. LTD.

Plot No 139, Roz-Ka-Meo Industrial Area, Sohna, Distt. Mewat (Nuh) 122103, Haryana, India.
E-Mail: sales@roopkoeppl.com, Web: www.roopkoeppl.com